

Screens

FilaSorb™ 12



Product Detail

Application Wall

Composition 100% polyester

MaterialFilaSorb™Recycled content60% minWeight2400gsmThickness12mm +/- 10%Dimensions1220 x 2800mm

Custom size available upon request

Sustainability



Made from 60% min. recycled content




Declare Red List Free (3rd Party Verified)



Generated using 40% solar energy



Recyclable at end of lifespan











Technical Data

Fire test method AS ISO 9705:2033 (according to AS 5637.7:2015 requirements) Group number Group 1 SMOGRARC (in m2/s2 x 1000) 0.93 Fire test method ASTM F48 Classification Class A Flame spread index 15 200 Smoke developed index Fire test method EN 13501-1: 2019 Classification B-s1, d0 Total VOC test method SCS-EC10.3-2014 v4.0 meeting standard CDPH/EHLB Standard Method v.1.2-2017 **Total VOC result** $\leq 0.5 \text{mg/m}^3$ Colorfastness test method ISO 105-B02 Rating 6-7

Guarantees

Warranty against defects 20 years*

Colorfastness warranty 20 years*

*conditions apply

QuickShip



QuickShip Standard (Made to Order)

Our standard made to order products have an approx.

2-3 week lead time from payment and order confirmation.

Acoustic Performance

Test AS ISO 354-2006: Acoustic - Measurement of sound absorption in a reverberation room

Installation method A, tested with no air gap

Rating ISO 11654-1997


method Acoustic – sound absorbers for use

in buildings – rating of sound absorption

Test results NRC 0.45 no air gap*

SAA 0.43 no air gap*

*results are for material only, some screen designs may not provide the same sound absorption rating due to the cut pattern variation.




Frequency (Hz)	125	250	500	1000	2000	4000	NRC
as no air gap	0.06	0.02	0.23	0.61	0.89	0.95	0.45

Performance Indices: **Noise Reduction Coefficient (NRC)** results represent the absorption coefficients measured at the one third octaves bands at 125, 250, 500, 1000, 2000 and 4000 Hz rounded to the nearest 0.05. Acoustic testing has been performed according to the methods mentioned above. Customisation of installation of the product could alter the results. **Sound Absorption Average (SAA)** indicates the absorption coefficient average for the twelve one-third octave bands ranging between 200 and 2500 Hz



Designs



Waterfall



Skyscraper

Sonar

Pyramid

Colorways

Light Reflectance Values (LRV), are **a measure of the percentage of visible and usable light that is reflected from a surface** when illuminated by a light source.



Mounting Methods

